



广微测
Gmicro Testing



201819000883



中国认可
国际互认
检测
TESTING
CNAS L1747

GUANGDONG DETECTION CENTER OF MICROBIOLOGY

REPORT FOR ANALYSIS

Report №.

2026SP01074R01E

Name of Sample

HALOGLAS Far-Infrared Energy Block

Applicant

HEBEI MSD GLASS TECHNOLOGY CO., LTD.

Test Type

Entrustment Test



Address: Building 66, No.100 , Xianlie Middle Road, Guangzhou, China

Postcode: 510070

Tel: +86 20 87137666

Fax : +86 20 87137668

Website : www.gddcm.com



广微测
Gmicro Testing

GUANGDONG DETECTION CENTER OF MICROBIOLOGY

REPORT FOR ANALYSIS



Report №.) 2026SP01074R01E

Verification Code: 7T8QA353

Name of Sample	HALOGLAS Far-Infrared Energy Block	Test Type	Entrustment Test
Applicant	HEBEI MSD GLASS TECHNOLOGY CO., LTD.	Address	JIAN SHE NAN STREET, DEVELOPMENT ZONE, HEJIAN CITY, HEBEI, CHINA.
Sample Source	Submitted for Testing by the Applicant	Sample Quantity	30 pieces
Spec and Lot № of Sample	_____	State and Characteristic	Nubbly
Sample Received Date	2026-02-02	Completion Date	2026-02-26
Item Tested	Antimicrobial activity		
Test Standard and Method	GB/T 30706-2014		
Test Conclusion	The test data of the sample(s) is attached to the page(s) of this report. Issue Date: 2026-02-26 (Official Seal) 检验检测专用章		
Remarks			

Editor: Hu Shaofang

Verifier: Chen Ling

Approver: Li Liangqiu



GUANGDONG DETECTION CENTER OF MICROBIOLOGY

ANALYSIS AND TEST RESULT

Report №.: 2026SP01074R01

Antimicrobial activity

1. Test method: GB/T 30706-2014

2. Test Result:

Test Organism	The number of bacteria on the inoculated treated samples at "0" contact time of control group (cfu/piece)	Under bright conditions the number of bacteria on the inoculated treated samples of control group (cfu/piece)	Under bright conditions the number of bacteria on the inoculated treated samples of test group (cfu/piece)	Under the dark conditions the number of bacteria on the inoculated treated samples of control group (cfu/piece)	The number of viable bacteria after the sample for photocatalysis was cultured under dark conditions (cfu/piece)	Antibacterial value under fluorescen (%)	Antibacterial rate R_{total} (%)
<i>Escherichia coli</i> AS1.90	9.6×10^4	7.0×10^6	1.8×10^2	7.8×10^6	5.6×10^6	99	99

Conclusion: The original sample was sent for testing. After cultivation, the antibacterial rate (R_{total}) against *Escherichia coli* was 99%, which is in line with the result determination of GB/T 30706-2014 (antibacterial rate (R_{total}) $\geq 99\%$, judged as having a strong antibacterial effect). It is determined that this sample has a strong antibacterial effect against *Escherichia coli* under the test conditions used.

(Blank below)



广 微 测

Gmicro Testing

Report №.: 2026SP01074R01E

Notice Items

1. The test report is invalid without the special stamp of testing and paging seal.
2. The test report is invalid without the signatures of the editor, the verifier and the approver.
3. The test report is invalid if being supplemented, deleted or altered.
4. Without prior written permission, the test report cannot be reproduced, except in full.
5. Unless otherwise stated , the results shown in this test report refer only to the sample(s) tested.
6. Any dispute of the test report must be raised to the testing institution within 15 days after the test report is received, exceeding which the dispute will not be accepted.
7. For the sample(s) submitted for testing, the sample information is provided by the applicant, and this testing institution is not responsible for its authenticity.

